



Protection is a concrete idea.



CBIS/Korfil HI-R CMU Fire Ratings

Type of Aggregate Used In CMU's	HI-R	HI-R	HI-R
	8 x 8 x 16 3.86	10 x 8 x 16 4.31	12 x 8 16 4.91
Calcareous or Siliceous Gravel	1 3/4 Hr Rating	2.0 Hr Rating	2 5/8 Hr Rating
Limestone, Cinders, or Unexpanded Slag	1 7/8 Hr Rating	2 1/4 Hr Rating	2 7/8 Hr Rating
Expanded Clay, Shale, or Slate	2 1/4 Hr Rating	2 7/8 Hr Rating	3 3/4 Hr Rating
Expanded Slag or Pumice	2 3/4 Hr Rating	3 3/8 Hr Rating	4.0+ Hr Rating

Type of Aggregate Used In CMU's	1/2 HI-R	1/2 HI-R	1/2 HI-R
	8 x 4 x 16 3.95	10 x 4 x 16 4.48	12 x 4 16 5.17
Calcareous or Siliceous Gravel	1 3/4 Hr Rating	2 1/4 Hr Rating	2 7/8 Hr Rating
Limestone, Cinders, or Unexpanded Slag	2.0 Hr Rating	2 1/2 Hr Rating	3 1/4 Hr Rating
Expanded Clay, Shale, or Slate	2 1/2 Hr Rating	3.0 Hr Rating	4.0 Hr Rating
Expanded Slag or Pumice	3.0 Hr Rating	3 1/2 Hr Rating	4.0+ Hr Rating

Type of Aggregate Used In CMU's	HI-R-H	HI-R-H	HI-R-H
	8 x 8 x 16 3.95	10 x 8 x 16 4.48	12 x 8 16 5.17
Calcareous or Siliceous Gravel	1 3/4 Hr Rating	2 1/4 Hr Rating	2 7/8 Hr Rating
Limestone, Cinders, or Unexpanded Slag	2.0 Hr Rating	2 1/2 Hr Rating	3 1/4 Hr Rating
Expanded Clay, Shale, or Slate	2 1/2 Hr Rating	3.0 Hr Rating	4.0 Hr Rating
Expanded Slag or Pumice	3.0 Hr Rating	3 1/2 Hr Rating	4.0+ Hr Rating

REFERENCES: National Concrete Masonry Association TEK 7-1C Fire Resistance Ratings of Concrete Masonry Assemblies

Concrete Block Insulating Systems
P.O. Box 1000
Freight House Road
West Brookfield, MA 01585-1000

508.867.4241
800.628.8476
Fax: 508.867.5702

www.cbisinc.com
E-mail: korfil@cbisinc.com
Member of NCMA and EPSMA

