



Protection is a concrete idea.

HI-R-H MASONRY UNITS* (UNGROUTED)

- UNITS - R_T Values (hr ft²F°/BTU) U-FACTOR (BTU/hr ft²F°)
 - HEAT CAPACITY (HC) (BTU/hr ft²F°)
 - EQUIVALENT THICKNESS (INCHES)

TYPE OF BLOCK (inches)	DENSITY OF CONCRETE BLOCK					
	Lbs/Cu ft					
	85	95	105	115	125	135
10 X 8 X 16 BLOCK						
R_T VALUE	16.97	15.67	14.34	13.13	11.93	10.73
U FACTOR	0.06	0.06	0.07	0.08	0.08	0.09
HEAT CAPACITY (HC)	5.47	6.02	6.66	7.21	7.83	8.48
EQUIVALENT THICKNESS	4.11	4.11	4.11	4.11	4.11	4.11
12 X 8 X 16 BLOCK						
R_T VALUE	18.03	16.73	15.39	14.15	12.91	11.66
U FACTOR	0.06	0.06	0.07	0.07	0.08	0.09
HEAT CAPACITY (HC)	5.57	6.16	6.75	7.43	8.02	8.61
EQUIVALENT THICKNESS	4.30	4.30	4.30	4.30	4.30	4.30

- * REFERENCES - www.cbisinc.com, Technical Library Section PDF File No. 316 (Development of HI-R Block U-factors)
 - National Concrete Masonry TEK No. 6-16A Heat Capacity (HC)
 - National Concrete Masonry TEK No. 7-1C Fire Resistance Rating of Concrete Masonry Assemblies

Insulated concrete blocks specified for any project must certify that the R-Values they publish comply with the calculation procedures outlined in the National Concrete Masonry "Thermal Catalog of Concrete Masonry Assemblies" which is based on The American Society of Heating, Refrigerating and Air-Conditioning Engineers Standard 90.1. Further, Concrete Block Insulating Systems certifies that the R-Values listed do comply with the above stated calculation procedure.

COMMONWEALTH OF MASSACHUSETTS
 DAVID L. NICKERSON
 18853
 REGISTERED PROFESSIONAL ENGINEER
 7/15 July 15

Concrete Block Insulating Systems
 P.O. Box 1000
 Freight House Road
 West Brookfield, MA 01585-1000

508.867.4241
 800.628.8476
 Fax: 508.867.5702

www.cbisinc.com
 E-mail: korfil@cbisinc.com
 Member of NCMA and EPSMA





Protection is a concrete idea.

HI-R-H MASONRY UNITS* (FULLY GROUTED)

UNITS - R_T Values (hr ft²F°/BTU) U-FACTOR (BTU/hr ft²F°)

- HEAT CAPACITY (HC) (BTU/hr ft²F°)

- EQUIVALENT THICKNESS (INCHES)

- GROUT DENSITY AT 140 LB PER Cu Ft

10 X 8 X 16 BLOCK						
R_T VALUE	16.41	15.11	13.70	12.57	11.37	10.17
U FACTOR	0.06	0.07	0.07	0.08	0.09	0.10
HEAT CAPACITY (HC)	15.20	15.80	16.30	16.90	17.50	18.00
EQUIVALENT THICKNESS	7.60	7.60	7.60	7.60	7.60	7.60
12 X 8 X 16 BLOCK						
R_T VALUE	17.62	16.32	14.98	13.74	12.50	11.25
U FACTOR	0.06	0.06	0.07	0.07	0.08	0.09
HEAT CAPACITY (HC)	19.50	20.10	20.80	21.50	22.10	22.80
EQUIVALENT THICKNESS	9.60	9.60	9.60	9.60	9.60	9.60

- * REFERENCES - www.cbisinc.com, Technical Library Section PDF File No. 316 (Development of HI-R Block Insulation) (R-Values)
 - National Concrete Masonry TEK No. 6-16A Heat Capacity (HC)
 - National Concrete Masonry TEK No. 7-1C Fire Resistance Rating of Concrete Masonry

Insulated concrete blocks specified for any project must certify that the R-Values they publish comply with the calculation procedures outlined in the National Concrete Masonry "Thermal Catalog of Concrete Masonry Assemblies" which is based on The American Society of Heating, Refrigerating and Air-Conditioning Engineers Standard 90.1. Further, Concrete Block Insulating Systems certified by The American Society of Heating, Refrigerating and Air-Conditioning Engineers shall certify that the R-Values listed do comply with the above stated calculation procedure.

COMMONWEALTH OF MASSACHUSETTS
 DAVID L. NICKERSON
 18853
 REGISTERED PROFESSIONAL ENGINEER
 7/13/15

Concrete Block Insulating Systems
 P.O. Box 1000
 Freight House Road
 West Brookfield, MA 01585-1000

508.867.4241
 800.628.8476
 Fax: 508.867.5702

www.cbisinc.com
 E-mail: korfil@cbisinc.com
 Member of NCMA and EPSMA